

Physica C: Superconductivity, 231(3-4): 367-371

## Bulk $2a \times 2b \times c$ Superstructure in TCNQ-treated (Bi, Pb)-2223 Cuprates

Liu, Chia-Jyi; Wu, X. J. ; Yamauchi, H.

### Abstract

By reaching (Bi, Pb)-2223 cuprate superconductors with TCNQ (7,7,8,8-tetracyanoquinodimethane) in a sealed and evacuated pyrex ampoule at 300°C for 14 days, we have observed a superstructure of  $2a \times 2b \times c$  in a bulk form according to X-ray diffraction and transmission electron microscope analyses. The origin of the  $2a \times 2b \times c$  superstructure could be attributed to an ordering of oxygen vacancies in the CuO<sub>2</sub> layers and also likely in the SrO layers. Electrical conductivity of this TCNQ treated (Bi, Pb)-2223 cuprate shows a metal-like temperature dependence with high resistivity (10<sup>2</sup>~10<sup>3</sup> Ω cm), and a relatively rapid resistivity drop at ca. 11.7 K.